

106



235-300°F (113-150°C) Cure Epoxy Film Adhesive

Typical applications

Aerospace
Sporting goods
Marine
Wind energy
Industrial

Out life

7 days at 70°F (21°C)

Shelf life

3 months at 40°F (4°C)
6 months at 0°F (-18°C)

Description

106 is a 235°F (113°C) to 300°F (150°C) cure, general purpose flame retardant epoxy film adhesive designed for bonding applications requiring high strengths from -67°F (-55°C) to 180°F (82°C).

Benefits/features

- Flame retardant
- Co-curable with most 250°F (120°C) curing prepregs
- FAR 25.853 Appendix F, Part I, (a)(1)(i) flammability requirements
- MMM-A-132B, Type I, Class 3, Group 3
- MIL-A-25463B, Type I, Class 1, Group 3

Variants

- 106-8: Self-adhesive

Application

106 is suited for structural and secondary bonding applications where flame retardant properties are required. Recommended for bonding substrates including, but not limited to, Nomex & aluminum honeycombs, metals, cured & uncured epoxy composites, balsa, and foams.

106 is supplied in standard film weights from 0.030 to 0.090 psf (150-450 gsm), either unsupported or on a variety of commercially available reinforcements, including:

- Non-woven polyester carrier (HC)
- Nylon mesh (N), and tricot (TR)
- Unsupported (U)
- Metal meshes for electrical management

Recommended processing conditions

106 can be cured at temperatures from 235°F (113°C) to 300°F (150°C), depending on part size and complexity. Low, medium, and high pressure molding techniques may be used for curing. Recommended cure cycle is 25psi (172kPa), 3°F (1.7°C)/min, ramp to 250°F (135°C), hold for 60 minutes, cool to <140°F (60°C).

Please contact your account manager or MCCFC technical support to discuss specific applications.



MITSUBISHI CHEMICAL
CARBON FIBER AND COMPOSITES

Technical Data Sheet



Neat resin (values are average and do not constitute a specification)

Property	Measured value
Gel time @ 275°F (135°C), minutes	3 – 5
Specific gravity	1.30
T _g (DMA, E'), °F (°C)	212 (100)

Mechanical data (values are average and do not constitute a specification)

NB106HC, 0.060 psf, preheated press 275°F, 1 hour, 25 psi


Property	Test method	-67°F (-55°C)	RT	180°F (82°C)
Lap shear strength, psi (MPa)*	ASTM D1002	3800 (26.2)	4400 (30.3)	3100 (21.3)
Flatwise tensile strength, psi (MPa)	ASTM C297	1200 (8.27)	1300 (8.96)	975 (6.72)
Flexural strength, lbs (kN)	ASTM C393	2800 (12.4)	2900 (12.9)	2400 (10.6)
CD peel strength, in-lbs/in (Nm/m)**	ASTM D1781	-	14 (62)	-

*MMM-A-132B, Type I, Class 3, Group 3 **MIL-A-25463B, Type I, Class 1, Group 3




106 Viscosity vs. temperature

TA - AR2000 parallel plate rheometer



Gel time vs. temperature



The information contained herein has been obtained under controlled laboratory conditions and are typical or average values and do not constitute a specification, guarantee, or warranty. Results may vary under different processing conditions or in combination with other materials. The data is believed to be reliable but all suggestions or recommendations for use are made without guarantee. You should thoroughly and independently evaluate materials for your planned application and determine suitability under your own processing conditions before commercialization. Furthermore, no suggestions for use or material supplied shall be considered a recommendation or inducement to violate any law or infringe any patent.

CORPORATE OFFICE
Composite Materials Division
1822 Reynolds Avenue
Irvine, CA 92614

Tel: (949) 253-5680
Fax: (949) 253-5692
www.mccfc.com
compositesales@mccfc.com

THE KAITEKI COMPANY

Mitsubishi Chemical Holdings Group